



THE EFFECT OF HEAT APPLICATION ON FLUORIDE RELEASE FROM ANTIBACTERIAL AGENT ADDED GLASS IONOMER CEMENT

ABSTRACT

Objectives: This study aimed to evaluate the effect of heat on the fluoride (F⁻) releasing ability of glass ionomer cement (GIC) when used in the conventional form and when combined with 5% cetylpyridium chloride (CPC).

Materials and Methods: Twenty (n=5; each group) GIC samples were prepared, with the experimental group comprising GIC combined with 5% CPC and the control group comprising GIC without 5% CPC. The samples were prepared by non-heating (NH) procedures (n = 10) or by heating (H) for 60 seconds (n = 10) with a Light Emitting Diode (LED). Fluoride releasing pattern was evaluated on days 1, 7, 15 and 30. Repeated measurements using two-way ANOVA and Fisher's LSD test were used for comparisons (p < 0.05).

Results: Interactions among the groups, application of heat, and the time at which F⁻ release was evaluated were analyzed (p < 0.001). There was no significant difference in F⁻ release in the NH control and experimental groups on days 1, 7 and 15; however a significant release was evident in the experimental group on day 30 (p=0.01). Significantly higher values were obtained in the H associated control group than in the experimental group on days 1 (p=0.026), 7 (p = 0.001), 15 (p=0.005) and 30 (p=0.028). Significantly increased values were obtained from days 1 to 30 by NH and H procedures for both the groups (p<0.001).

Conclusions: Heating in the control and experimental groups showed an increased F⁻ releasing pattern. The fluoride release on 60 seconds of heating GIC containing 5% CPC, can have acceptable values for up to 30 days. The increased F⁻ releasing pattern after the heating is believed to be promising for antibacterial GIC combinations.

Key words: Anti-bacterial agents, glass ionomer cement, fluorides, heating.

 *Ayça Kurt¹
 Tamer Tüzüner²
 İlkey Altıntepe³
 Sema Aydınoglu¹
 Münevver Sökmen⁴

ORCID IDs of the authors:
A.K. 0000-0003-4762-7495
T.T. 0000-0001-5817-5928
İ.A. 0000-0002-2630-5254
S.A. 0000-0003-1490-8645
M.S. 0000-0002-7671-4160

¹ Department of Pedodontics, Faculty of Dentistry, Recep Tayyip Erdoğan University, Rize, Turkey

² Department of Pedodontics, Faculty of Dentistry, Karadeniz Technical University, Trabzon, Turkey

³ Department of Pedodontics, Faculty of Dentistry, Akdeniz University, Antalya, Turkey

⁴ Bioengineering Department, Faculty of Engineering Architecture, Konya Gıda ve Tarım University, Konya, Turkey

Received : 26.12.2018
Accepted : 01.04.2019

INTRODUCTION

Although dental caries is one of the most common oral diseases worldwide, it can neither be treated completely in the underdeveloped societies nor can become a priority in the developing and industrialized countries over social, economic, political and other issues.^{1,2} According to Blinkhorn and Davies³, the main reasons for inability to provide dental care are expensive dental equipment and inability to meet the demand for a highly trained staff. In 1994, the atraumatic restorative treatment technique (ART) was discovered by the World Health Organization to overcome these difficulties.⁴ In ART, which is a form of mostly painless restorative treatment, cavitations are restored with a biocompatible material that does not cause bacterial invasion. Glass ionomer cement (GIC) is generally preferred for this treatment because of its chemical attachment to enamel and dentin, fluoride release and the ease of use.⁵ Despite numerous advantages of GIC as a restorative material, it has a few disadvantages in terms of secondary cavities and poor mechanical properties.⁶

There are numerous methods with modified properties used to overcome the disadvantageous of GIC. Materials such as routine hydroxyapatite, bioactive glass and strontium have been added to improve the physical and antibacterial (AB) properties of GIC.⁷⁻⁹ It has been reported^{10,11} that bactericidal materials such as chlorhexidine (CHX), have been used in a variety of studies, in which the AB efficiency of GICs has been observed to increase. In addition, the use of materials such as cetrimide (CT), cetylpyridinium chloride (CPC) and benzalkonium chloride (BC) from quaternary ammonium compounds (QAC) in combination with GIC are evaluated because their chemical properties are similar to those of CHX with AB activity.¹⁰⁻¹⁴ The CPC, used in this study is a cationic QAC and an antiseptic.¹⁵⁻¹⁶

One of the most important advantages of GICs is the property of fluoride release. The fluoride ion (F^-) can increase the ambient pH and prevent acidity by inhibiting the carbohydrate metabolism of the surrounding bacteria. This process is called buffering and is believed to be useful in the prevention of dental caries in future.¹⁷ It is stated

that AB agents alter the physical properties of the glass ionomer and even reduce F^- release and that the interaction between cationic molecules and F^- causes less soluble salt precipitation. Therefore, studies aim to achieve the F^- releasing ability of the modified GIC similar to that of the original GIC.¹⁸

When an AB agent is added to contents GIC, its physical and chemical properties may weaken. During the curing process of the material, it is possible to shorten the initial period of the curing reaction by applying heat with a light-emitting diode (LED), thus keeping the process, in which it is susceptible to moisture, as short as possible. This aids in preventing potential weakening of the physical and chemical properties of GIC after AB addition and to further strengthen its existing properties.¹⁹

The aim of this research was to evaluate F^- release of CPC added conventional GIC under the effect of heat application.

MATERIALS AND METHODS

In this study, 20 GIC samples (3M ESPE-Ketac™ Molar Easymix), with and without 5% CPC (Amresco, Ohio, USA), were used to prepare discs with 10 mm diameter and 2 mm thickness. The experimental group comprised GIC combined with 5% CPC in the powder form weighed using microbalances. Heat (H) generated by LED (3M ESPE, Germany) was applied to 10 samples for 60 seconds whereas no heat (NH) was applied to the 10 samples. The sample discs were placed in plastic cylindrical containers of diameter 32 mm, and height 50 mm, which contained 5 ml deionized water (pH of approximately 7). The samples were incubated at 37°C in the oven (Nüve-FN 500). Solutions of 100 ppm, 10 ppm, 1 ppm, 0.1 ppm, and 0.01 ppm were prepared by diluting 100 ppm of standard fluoride solution (Thermo Orion, Indonesia) with deionized water. A calibration procedure was performed on the F^- selective electrode (Thermo Orion, Indonesia) before measurement, and the values obtained by measuring these standards were recorded. To measure F^- in the test samples, GIC discs were transferred into a new plastic tube and put into a drying-oven by adding 5 ml deionized water; 0.5 ml ionic strength stabilizing total ionic strength

adjustment buffer (TISAB) III solution (Thermo Orion) was added to the liquid of the other 5 ml test sample. Fluoride measurements were performed using an ion meter (Thermo Orion, Indonesia) at room temperature. Cumulative fluoride release values on the 1st, 7th, 15th and 30th days were observed. Calibration curves were generated by calculating the data obtained with the known standard values. The data obtained from the test samples were calculated according to this curve. The results were evaluated as $\mu\text{g}/\text{mm}^2$ after calculating the amount of F^- released from the unit area on the sample surface.

Statistical Evaluation

Statistical Package for Social Sciences [(SPSS) 17.0 Windows (SPSS Inc. Chicago, Ill., USA)] was used for statistical evaluation. Two-way ANOVA and Fisher's LSD test were used for repeated measurements in statistical evaluation ($p < 0.05$). The confidence interval was set at 95%.

RESULTS

Interactions among the time, at which F^- release was recorded, application of heat and the study groups exhibited statistically significant values ($p < 0.01$, Table 1).

Table 1. Interaction effects of repeated measurements of two-way ANOVA

	Type III sum squares	df	Mean square	F	p value
Time	2.687	3	0.896	436.279	<i>p < 0.001</i>
Time-Group	0.16	3	0.005	2.593	<i>0.063</i>
Time-Heating	0.147	3	0.049	23.946	<i>p < 0.001</i>
Time-Group-Heating	0.70	3	0.023	11.421	<i>p < 0.001</i>

When F^- release values on the 1st, 7th, 15th and 30th days were compared between the NH control and experimental groups, no statistically significant difference was found ($p > 0.05$) on the 1st ($p = 0.33$), 7th ($p = 0.14$) and 15th ($p = 0.77$) days; however, on

the 30th day, the increase in fluoride release was statistically significant in the experimental group compared with that in the control group ($p = 0.01$; $p < 0.05$; Table 2).

Table 2. Differences between non-heated control and non-heated experimental groups at different time periods

	1 st day mean \pm sd	7 th day mean \pm sd	15 th day mean \pm sd	30 th day mean \pm sd
Control (n=5)	0.05 \pm 0.01	0.20 \pm 0.03	0.25 \pm 0.04	0.36 \pm 0.05
Experimental (n=5)	0.08 \pm 0.02	0.28 \pm 0.06	0.38 \pm 0.09	0.56 \pm 0.13
p value	<i>0.33</i>	<i>0.14</i>	<i>0.77</i>	<i>0.01</i>

*Significantly different values were obtained between control and experimental groups on the 30th day ($p = 0.01$).

When changes between the H control and experimental groups were evaluated, it was found that the values were statistically significant (Table 3) on the 1st ($p = 0.026$; $p < 0.05$), 7th ($p = 0.001$; $p < 0.01$), 15th ($p = 0.005$; $p < 0.01$) and 30th ($p = 0.028$; $p < 0.05$) days. At all these times, more F^- was released in the control group than in the experimental group. Significantly higher values

were observed after the H procedures than after the NH procedures on the 1st, 7th, 15th and 30th days for the control (for all; $p < 0.001$, Table 4) and on the 1st ($p < 0.001$), 7th ($p = 0.003$), 15th ($p = 0.011$) and 30th days ($p = 0.029$) for the experimental groups, individually (Table 5).

Table 3. Differences between heated control and heated experimental groups at different time periods

	1 st day mean \pm sd	7 th day mean \pm sd	15 th day mean \pm sd	30 th day mean \pm sd
Control (n=5)	0.26 \pm 0.06	0.68 \pm 0.10	0.80 \pm 0.11	0.93 \pm 0.07
Experimental (n=5)	0.20 \pm 0.04	0.47 \pm 0.12	0.58 \pm 0.15	0.75 \pm 0.19
p value	<i>0.026</i>	<i>0.001</i>	<i>0.005</i>	<i>0.028</i>

*Significant differences were found between control and experimental groups on the 1st ($p < 0.05$), 7th ($p < 0.01$), 15th ($p < 0.01$) and 30th days ($p < 0.05$).

Table 4. Time-dependent variation in fluoride release in control groups

	Control				<i>p</i> value
	1 st day mean±sd	7 th day mean±sd	15 th day mean±sd	30 th day mean±sd	<i>p</i> <0.001; for all comparisons
Heated	0.26±0.06 ^{A,a}	0.68±0.10 ^{B,a}	0.80±0.11 ^{C,a}	0.93±0.07 ^{D,a}	(<i>p</i> ^{A-B,A-C,A-D,B-C,B-D,C-D} <0.01)
Non-heated	0.05±0.01 ^{E,b}	0.20±0.03 ^{F,b}	0.25±0.04 ^{G,b}	0.36±0.05 ^{H,b}	<i>p</i> <0.001; for all comparisons (<i>p</i> ^{E-F,E-G,E-H,F-G,F-H,G-H} <0.01)

*A statistically significant increase was observed in non-heated control groups from day 1st to 30th (p<0.01).

*A statistically significant increase was observed in heated control group from day 1st to 30th (p<0.001).

*The fluoride release in the control group increased at a statistically significant level from day 1st to 30th with the application of heat (pa-b<0.001, p<0.05).

Table 5. Time dependent alterations in fluoride release for experimental group

	Experimental				<i>p</i> value
	1 st day Mean±sd	7 th day mean±sd	15 th day mean±sd	30 th day mean±sd	<i>P</i> ^{a-b} =0.002 <i>P</i> ^{a-c} =0.002 <i>P</i> ^{a-d} =0.001 <i>P</i> ^{b-c} =0.003 <i>P</i> ^{b-d} =0.001 <i>P</i> ^{c-d} <0.001
Heated	0.20±0.04 ^{a,A}	0.47±0.12 ^{b,C}	0.58±0.15 ^{c,E}	0.75±0.19 ^{d,G}	<i>P</i> ^{e-f} =0.001 <i>P</i> ^{e-g} =0.001 <i>P</i> ^{e-h} =0.001 <i>P</i> ^{f-g} =0.001 <i>P</i> ^{f-h} =0.001 <i>P</i> ^{g-h} =0.001
Non-heated	0.08±0.02 ^{e,B}	0.28±0.06 ^{f,D}	0.38±0.09 ^{g,F}	0.56±0.13 ^{h,H}	

*Statistically significant increase was observed in heated experimental groups from day 1st to 30th (p<0.01).

*The fluoride release in the experimental group increased at a statistically significant level from day 1st to 30th with the application of heat (pA-B<0.001, pC-D=0.003, pE-F=0.011, pG-H=0.029, p<0.05).

There was a statistically significant increase in F⁻ release from days 1 to day 30 in NH and H control groups (p < 0.001; Table 4) and experimental groups (Table 5, Figure 1).




Figure 1. Time dependent alterations in fluoride release in all groups

DISCUSSION

Heating of samples in the control and experimental groups showed an increased F⁻ release pattern. The fluoride release from GIC containing 5% CPC on heating for 60 seconds could have acceptable increased values for up to 30 days. McComb, Ericson,²⁰ DeSchepper *et al.*²¹ and Vermeersch *et al.*²² suggested that GIC is antimicrobial because of F⁻ release and/or acidity, but the results of previous investigations about the AB effects of both F⁻ and low pH are

controversial.^{23,24} Furthermore, the reduction in bacterial counts obtained by placing conventional GICs in cavities is not reliable; therefore, AB agent-modified GICs would provide an alternative approach.^{10,11,25} The combination of GICs and AB agents, particularly QACs, has been studied in previous studies.^{11,12,26} However, it has been pointed out that the AB agents alter the physical properties of the glass ionomer.²⁷ The interaction between the cationic molecules and F⁻ ions has been reported to cause less soluble salt precipitation. Thus, studies aim to achieve a F⁻ releasing ability of the modified GIC, similar to that of the original GIC.^{12,14,18}

In experimental studies, ion-selective electrodes are widely used in the analysis of F⁻ ions, because they are practical to use and yield accurate results when used in accordance with the rules.^{18,28,29} Total ionic strength adjustment buffer solution is used in the studies on F⁻ ion analysis for GICs. The buffer solution is added to control pH and prevent the formation of F⁻ ion complex structure.^{28,29}

In the NH control and experimental groups in our study, although more F⁻ was released in the experimental group at all the times, only the value

on the 30th day was statistically significant. The fluoride release in the experimental and control groups increased by a statistically significant level over time. Tüzüner *et al.*³⁰ evaluated the amount of F⁻ ions released on the 1st, 7th, 15th and 30th days in an experimental group using a mixture of Fuji IX, Ketac Molar powder, 2.5% CHX, and 2.5% CT powder and in the control group using Fuji IX and Ketac Molar with no AB agent. As a result, less F⁻ ions were released in the experimental groups that were combined with an AB agent at all the times compared with the control group, but this did not cause a statistically significant difference. In addition, there was a decrease in the F⁻ ion release in all the groups over time. Elsaka *et al.*³¹ investigated the cumulative F⁻ release and AB properties of modified GIC on the 1st, 7th and 28th days in their study, in which they added AB-effective titanium-dioxide (TiO₂) nanoparticles to conventional GIC. Similar release patterns were observed between the control group excluding titanium dioxide and experimental group. The highest release was observed during the first 24 hours, and the values declined over time. There was no statistically significant difference between the experimental and control groups in terms of the cumulative F⁻ release pattern. Hoszek and Ericson¹⁸ found that F⁻ release was lower in the experimental group than in the control group on addition of 10% CHX to GIC. However, they reported no statistically significant difference between the experimental and control groups in terms of F⁻ ion release levels ($p > 0.05$) and predicted that poorly soluble salt precipitates resulted from the interaction of cationic molecules and F⁻ ions resulting in this situation. The lack of statistically significant differences between the experimental and control groups in these three studies is consistent with the fact that the F⁻ release values on the 7th and 15th days in this study do not result in a statistically significant difference between the control and experimental groups; conversely, the decreasing F⁻ release values over time and increased F⁻ release in the control group contradicted the results of this study. Hu *et al.*³² found that the F⁻ release values of GIC modified with epigallocatechin-3-gallate (EGCG) and CHX did not show any significant difference between the

control and experimental groups, and reported that F⁻ release was the highest in the GIC + CHX group and lowest in the control group at the 24th hour after hardening, and this was parallel with the higher F⁻ release in the experimental group in our study. All the groups showed a decrease toward the 7th day. However, the F⁻ values on the 7th day were measurable. The decreasing F⁻ values contradicted the results of our study.

When we evaluated the effect of heat application on the groups in terms of the F⁻ release, the values in the control group were higher than those in the experimental group at a statistically significant level at all the times. As in the NH experimental and control groups, there was a significantly increasing F⁻ release over time in the H groups. On analyzing the control and experiment groups individually, we found that heat application caused significantly more F⁻ release. As far as we have reviewed the previous literature, there have been no studies investigating how heat application affects F⁻ release in GIC. However, there have been many studies exhibiting how the physical and chemical properties of conventional GICs and other dental materials are affected by radiant heat application.³³⁻³⁵ Tolidis *et al.*³⁴ examined the effects of radiant heat and ultrasonic heat applied by LED on GIC in their study with working groups. No heat treatment was applied in the control group, and radiant heat with LED was applied for 2 minutes and ultrasound for 55 seconds in the experimental group. The fluoride release values on the 7th, 14th and 28th days was assessed. The radiant heat applied during hardening reduces the release of F⁻. Furthermore F⁻ release decreased and surface hardness increased after ultrasonic treatment. Rafeek³⁵ applied only heat and heat along with pressure, both on conventional and resin-modified GICs and investigated the effect of these treatments on some physical characteristics of GICs and F⁻ release. The presence of heat was found to produce no significant result on conventional GIC; however, it reduced the release of F⁻ in resin-modified GIC. It is thought that the F⁻ release decreases whereas the physical properties of the resin modified by the heat application strengthen in accordance to the study limitations.

When we compared the unmodified control group of our study with all those of the studies mentioned above, we found that the reduced F⁻ release caused by heat application was not consistent with the results of our study. It may be considered that the differences in all F⁻ release patterns in the NH control/ experimental and H control groups that contradict with the literature are owing to the experimental variables in *in-vitro* studies, such as the internal structure of the material, including the composition, geometric structure, solubility, and porosity of the material used, the powder/ liquid ratio during the preparation, the amount and size of the sample, ambient temperature, surface applications, such as Vaseline or varnish on the material, ambient pH/ volume, different measurement methods, and other unknown factors.^{18,25,36}

However, compared with the previous studies, it can be considered that heat application may increase F⁻ release from the GIC combined with antibacterial materials, and this may be beneficial and promising for future studies.

CONCLUSIONS

As a result of our research conducted under *in-vitro* conditions, a significant increase in fluoride release in both conventional and GICs modified with an antibacterial agent at all time periods, as a result of heat application, can be considered promising for the fluoride release levels of GIC materials and future research. According to the results, when GIC is used in the ART techniques 60 seconds of heat administration will reduce the decay level occurring at the bottom of the face and teeth with binding surface are promising in clinical be said.

ACKNOWLEDGEMENTS

None

CONFLICT OF INTEREST

None

Antibakteriyel Ajan İlave Edilen Cam İyonomer Simanda Isı Uygulamasının Florür Salımına Etkisi **ÖZ**

Amaç: Çalışmanın amacı konvansiyonel yapıda olan ve %5 cetylpyridium chloride (CPC) ile kombine edilen cam iyonomer simanda (CİS) florür (F⁻) salımına, ısının

etkisini değerlendirmektir. **Gereç ve Yöntemler:** %5 cetylpyridium chloride (CPC) ile kombine edilen deney ve %5 CPC içermeyen kontrol grubundan oluşan yirmi adet (n=5; her grupta) CİS örneği hazırlandı. Örneklerden 10 tanesine ısı uygulanmadı (IU), diğer 10 tanesine ise 60 sn Light Emitting Diode (LED) ışık kaynağı ile oluşturulan ısı etkisi (IE) altında uygulama yapıldı. Bir, 7, 15 ve 30. günlerdeki F⁻ salımı gözlemlendi. Karşılaştırmalar için iki yönlü ANOVA ve Fisher's LSD testinin tekrarlanan ölçümleri kullanıldı (p<0,05).

Bulgular: Florür salımının değerlendirildiği grup, ısı ve zaman değişkenleri arasındaki etkileşimler analiz edildi (p<0,001). Bir, 7 ve 15. günlerdeki IU kontrol ve deney gruplarında F⁻ salımı açısından anlamlı bir fark yoktu, ancak 30. günde deney grubunda anlamlı bir F⁻ salımı vardı (p=0,01). Isı etkisi altında kontrol grubu için 1 (p=0,026), 7 (p=0,001), 15 (p=0,005) ve 30. (p=0,028) günlerde deney grubuna kıyasla anlamlı olarak daha yüksek değerler elde edildi. Hem IU hem de IE altındaki her iki grupta da 1 ila 30 gün arasında anlamlı olarak artan değerler elde edildi (p<0,001). **Sonuç:** Isı etkisinin kontrol ve deney gruplarında F⁻ salımını arttırdığı gözlemlendi. 60 sn ısı uygulanan %5 CPC eklenen CİS F düzeyinde 30. güne kadar kabul edilebilir bir artış gözlemlendi. Isı uygulaması; antibakteriyel eklenmiş CİS'lerin florür salım düzeyleri için ümit vaat edicidir. **Anahtar kelimeler:** Anti-bakteriyel ajanlar, cam iyonomer siman, florürler, ısıtma.

REFERENCES

1. Ismail AI. Reactor paper: minimal intervention techniques for dental caries. J Public Health Dent 1996; 56: 155-160.
2. Mjor IA, Gordan VV. A review of atraumatic restorative treatment (ART). Int Dent J 1999; 49:27-131.
3. Blinkhorn AS, Davies RM. A continued need worldwide. Int Dent J 1996; 46: 119-125.
4. Pilot T. Introduction-ART from global perspective. Community Dent Oral Epidemiol 1999; 27: 421-422.
5. Chkir AF, Salem KB, Volu KA. Atraumatic restorative treatment and glass ionomer sealants in Tunisian children: survival after 3 years. East Mediter Health J 2002; 23: 200-204.
6. van Amerongen WE. Dental caries under glass ionomer restorations. J Public Health Dent 1996; 56: 150-154.

7. Gu YW, Yap AU, Cheang P, Khor KA. Effects of incorporation of HA/ZrO₂ into glass ionomer cement (GIC). *Biomaterials* 2005; 26:13-20.
8. Yli-Urpo H, Lassila LV, Narhi T, Vallitu PK. Compressive strength and surface characterization of glass ionomer cements modified by particles of bioactive glass. *Dent Mater* 2005; 21: 201-209.
9. Dabsie F, Gregoire G, Sixou M, Sharrock P. Does strontium play a role in the cariostatic activity of glass ionomer? Strontium diffusion and antibacterial activity. *J. Dent* 2009; 37: 554-559.
10. Botelho MG. Inhibitory effects on selected oral bacteria of antibacterial agents incorporated in a glass ionomer cement. *Caries Res* 2003; 37: 108-114.
11. Ribeiro J, Ericson D. In vitro antibacterial effect of chlorhexidine added to glass-ionomer cements. *Scand J Dent Res* 1991; 99: 533-540.
12. Sanders BJ, Gregory RL, Moore K, Avery DR. Antibacterial and physical properties of resin modified glass-ionomers combined with chlorhexidine. *J Oral Rehabil* 2002; 29: 553-558.
13. Botelho MG. The antimicrobial activity of a dentin conditioner combined with antibacterial agents. *Oper Dent* 2005; 30: 75-82.
14. Botelho MG. Compressive strength of glass ionomer cements with dental antibacterial agents. *Sadj* 2004; 59: 51-53.
15. Albert-Kiszely A, Pjetursson BE, Salvi GE, Witt J, Hamilton A, Persson GR, Lang NP. Comparison of the effects of cetylpyridinium chloride with an essential oil mouth rinse on dental plaque and gingivitis - a six-month randomized controlled clinical trial. *J Clin Periodontol* 2007; 34: 658-67.
16. Haps S, Slot DE, Berchier CE, Van der Weijden GA. The effect of cetylpyridinium chloride-containing mouth rinses as adjuncts to toothbrushing on plaque and parameters of gingival inflammation: a systematic review. *Int J Dent Hyg* 2008; 6: 290-303.
17. Nicholson JW, Czarnecka B, Limanowska-Shaw H. The long-term interaction of dental cements with lactic acid solutions. *J Mater Sci Mater Med* 1991; 10: 449-452.
18. Hoszek A, Ericson D. In vitro fluoride release and the antibacterial effect of glass ionomers containing chlorhexidine gluconate. *Oper Dent* 2008; 33: 696-701.
19. Prabhakar AR, Prahlad D, Kumar SR. Antibacterial activity, fluoride release, and physical properties of an antibiotic- modified glass ionomer cement. *Pediatr Dent* 2013; 35: 411-415.
20. McComb D, Ericson D. Antimicrobial action of new, proprietary lining cements. *J Dent Res* 1987; 66: 1025-1028.
21. DeSchepper EJ, White RR, von der Lehr W. Antibacterial effect of glass ionomers. *Am J Dent* 1989; 2: 51-56.
22. Vermeersch G, Leloup G, Delmée M, Vreven J. Antibacterial activity of glassionomer cements, compomers and resin composites: relationship between acidity and material setting phase. *J Oral Rehabil* 2005; 32: 368-374.
23. Tam LE, Chan GP, Yim D. In vitro caries inhibition effects by conventional and resin-modified glass-ionomer restorations. *Oper Dent* 1997; 22: 4-14.
24. Miller BH, Komatsu H, Nakajima H, Okabe T. Effect of glass ionomer manipulation on early fluoride release. *Am J Dent* 1995; 8: 182-186.
25. Takahashi Y, Imazato S, Kaneshiro AV, Ebisu S, Frencken JE, Tay FR. Antibacterial effects and physical properties of glass-ionomer cements containing chlorhexidine for the ART approach. *Dent Mater* 2006; 22: 647-652.
26. Imazato S. Antibacterial properties of resin composites and dentin bonding systems. *Dent Mater* 2003; 19: 449-457.
27. Towler MR, Bushby AJ, Billington RW, Hill RG. A preliminary comparison of the mechanical properties of chemically cured and ultrasonically cured glass ionomer cements, using nano-indentation techniques. *Biomaterials* 2001; 22: 1401-1406.
28. Asmussen E, Peutzfeldt A. Long-term fluoride release from a glass ionomer cement, a compomer, and from experimental resin composites. *Acta Odontol Scand* 2002; 60: 93-97.
29. Lucas ME, Arita K, Nishino M. Toughness, bonding and fluoride-release properties of hydroxyapatite-added glass ionomer cement. *Biomaterials* 2003; 24: 3787-3794.
30. Tüzüner T, Kuşgöz A, Er K, Taşdemir T, Buruk K, Kemer B, Saray O. Antibacterial activity and physical properties of conventional glass-ionomer cements containing chlorhexidine diacetate/ cetrinide mixtures. *J Esthet Rest Dent* 2011; 23: 46-55.
31. Elsaka SE, Hamouda IM, Swain MV. Titanium dioxide nanoparticles addition to a conventional glass-

ionomer restorative: influence on physical and antibacterial properties. *J Dent* 2011; 39: 589-598.

32. Hu J, Du X, Huang C, Fu D, Ouyang X, Wang Y. Antibacterial and physical properties of EGCG-containing glass ionomer cements. *J Dent* 2013; 41: 927-934.

33. Dionysopoulos D, Tolidis K, Gerasimou P, Sfeikos T. Effect of Three Clinical Curing Treatments on Fluoride Release and Surface Hardness of Glass-Ionomer Cements. *Int J Periodontics Restorative Dent* 2017;37:197-203.

34. Tolidis K, Dionysopoulos D, Gerasimou P, Sfeikos T. Effect of radiant heat and ultrasound on fluoride release and surface hardness of glass ionomer cements. *J Appl Biomater Funct Mater* 2016 2;14:463-469.

35. Rafeek RN. The effects of heat treatment on selected properties of a conventional and a resin-modified glass ionomer cement. *J Mater Sci Mater Med* 2008; 19: 1913-1920.

36. De Witte AM, De Maeyer EA, Verbeeck RM, Martens LC. Fluoride release profiles of mature restorative glass ionomer cements after fluoride application. *Biomaterials* 2000; 21: 475-482.